



Date: 18.03.2011
Date of test: 11.02.2011
GOV-0807

CUSTOMER :
MULTIFARB SP Z.O.O.
UL.HANDLOWA 4
35-103 RZESZÓW
POLONIA
PRODUCT : **RWS-7162**
DESCRIPTION... : TGIC FREE POLYESTER SATIN GREY
COLOUR : GREY
RAL : 7016
BATCH : 83534
TOXICITY : S0
C.SCHED :
Nr. LICENCE .. : QUALICOAT P-0421

TEST

=====

SPECIFICATIONS

=====

RESULTS

=====

*** POWDER PROPERTIES ***

Thickness	UNE 48031-80	60 - 80 µm	70 µm
Particle size Mean	Average	44,000 - 52,000 µm	48,100 µm
Particle size < 10	10 µm	%	6,00 %
Particle size > 100	100 µm	%	5,23 %
Curing	200 °C	15 min	15 min
Application System			Triboeléctric / Electrostático
Application Properties			Good

*** FILM PROPERTIES ***

Aspect			GOOD
Gloss 60°	UNE EN ISO 2813	60 - 70 %	66 %
Colour DE			0,46
Colour DL			0,28
Colour Da			0,26
Colour Db			0,26
Mandrel Folding	UNE EN ISO 1519	< = 5 mm	5 mm
Test(Stamping)	UNE 48183-84	> = 1 mm	1 mm
Direct Impact	UNE-EN ISO 6272	> = 70 cm	70 cm
Inverse Impact	UNE-EN ISO 6272	> = 70 cm	70 cm
Adhesion	UNE EN ISO 2409		GTO

